

Artikel 25

by Parabelem Tinno Dolf Rompas

Submission date: 01-May-2020 11:50PM (UTC+0700)

Submission ID: 1313268284

File name: rom_Recycled_of_Zinc_Anode_used_as_a_Corrosion_Preventing....pdf (590.73K)

Word count: 2232

Character count: 12118

PAPER • OPEN ACCESS

Characteristics from Recycled of Zinc Anode used as a Corrosion Preventing Material on Board Ship

9
To cite this article: B Barokah *et al* 2018 *IOP Conf. Ser.: Mater. Sci. Eng.* **306** 012021

View [the article online](#) for updates and enhancements.

Related content

- [Design check against the construction code \(DNV 2012\) of an offshore pipeline using numerical methods](#)
L C Stan, I Climescu and D D Velcea
- 6
- [search on the corrosion inhibitors of zinc in hydrochloric acid](#)
C X Sun, Y M Chen, H W Xu *et al.*
- 10
- [Nanostructured nickel electrodes using the Tobacco mosaic virus for microbattery](#)
- 16
- [ications](#)
Konstantinos Gerasopoulos, 14
McCarthy, Elizabeth Royston *et al.*

Characteristics from Recycled of Zinc Anode used as a Corrosion Preventing Material on Board Ship

B Barokah¹, S Semin^{2*}, D D Kaligis¹, J Huwae¹, M Z Fanani¹ and P T D Rompas³

¹Politeknik K¹³tan dan Perikanan Bitung 95226, North Sulawesi, Indonesia

²Departement of Marine Engineering, Institut Teknologi Sepuluh Nopember Surabaya 60111, Indonesia

³Universitas Negeri Manado, Tondano 95618, Sulawesi Utara, Indonesia

*semin@its.ac.id

Abstract. The objective of this research is to obtain the values of chemical composition, electrochemical potential and electrochemical efficiency. Methods used were experiment with physical tests conducted in metallurgical laboratory and DNV-RP-B401 cathode protection design DNV (Det Norske Veritas) standard. The results showed that the composition of chemical as Zinc (Zn), Aluminium, Cadmium, Plumbumb, Copper and Indium is suitable of standard. The values of electrochemical potential and electrochemical efficiency were respectively. However it can be concluded that the normal meaning of recycled zinc anode with increasing melting temperature can produce zinc anode better than original zinc anode and can be used as cathode protection on board ships. This research can assist in the management of used zinc anode waste, the supply of zinc anodes for consumers at relatively low prices, and recommendations of using zinc anodes for the prevention of corrosion on board ship.

1. Introduction

Corrosion is a degradation of a substance or its nature due to its interaction with the environment. The corrosion mechanism is very damaging to materials and equipment in the industrial structure [1]. Corrosion is assumed to be the result of three sequential processes: degradation of the paint layer, pitting point formation, and pitting point progress. Corrosion rate can be identified quantitatively. Modeling probabilistic corrosion by analyzing existing data collected from plate thickness measurements. Data is verified by comparing the approximate behavior of corrosion and dispersion progress with actual data [2].

The corrosion rate of the sacrificial anodes of Al-Zn-In-Mg-Ti in sea water is higher than that of sea mud [3]. Many types of corrosion such as pitting corrosion is a material failure mechanism of a component that occurs due to an aggressive environmental influence, this is indicated by the presence of chloride and sulphide that accelerate the corrosion process above 50-55°C [4].

Steel is a metal that is widely used in marine ship structures that are strongly influenced by moisture and atmospheric ocean temperatures resulting in extremely vulnerable corrosion. So it is necessary to prevent by using sacrificial anode to reduce the corrosion rate. The marine environment is a corrosive environment which is as a factor that greatly affects metal degradation. Corrosion can occur continuously if there is no corrosion precaution on the metal [5]. Treatment needs to be done to minimize corrosion. There are several methods to protect material against corrosion commonly known as cathodic



protection method (CP) and cathodic prevention (CPrev) [6]. Voltage generated by the anode can function as an antifouling on the hull of the ship [7].

Generally the conventional anode used as a sacrificial anode on board is the Aluminum-Zinc-Indium (Al-Zn-In) alloy. This type of alloy has high efficiency and high potential protection in the seawater environment [8]. Various types of sacrificial anodes such as Al-Zn-In-Mg-Ti have the same relative dissolution. Several factors affecting corrosion rates are conductivity and dissolved oxygen in seawater [3]. When electrochemical testing is applied, sampling for testing shall be carried out for each heat produced, and has to be standardized. Unless agreed by others, the testing shall be carried out according to the procedure in standard and the following acceptance criteria shall apply for Zinc based anodes electrochemical capacity: minimum 780 Ah/kg, closed circuit potential: ≤ -1.00 V [9].

Zinc is a type 4 metal widely used as a sacrificial anode to protect iron from rust as well as aluminum and magnesium. The working principle of the anode is metals such as zinc, aluminum, and magnesium, because it is more reactive to the carat element and has a lower oxidation point than the iron so that when mounted on other metals such as iron, it first reacts to the rust and neutralize the rust before attacking the iron. Anode can work because it is made of zinc, aluminium, and magnesium metal which is more active against corrosion than iron so that if installed adjacent to the arrangement based on the correct calculation, then the rust will go to the anode first. Due to its inherent nature, after a certain period the anode should be replaced to ensure maximum protection. The zinc anode work will increase naturally to a maximum level to protect the hull from corrosion caused by the high salinity content of seawater present in the ocean waters [10]. Recycling used products from metal to be used again has been done in many western countries [11]. Recycling allows the recovery of metal parts, reducing the resource requirements of the natural environment. Recycling will save natural resources, reduce pollute, and save energy [12].

2. Methods

The method used in this research is experimental method that goes through several stages: conducting test of making zinc anode by recycling used zinc anode; laboratory testing of recycled zinc anode product to obtain value of chemical composition, electrochemical potential value and electrochemical efficiency value. Tools and materials such as: Furnace, Brander, Cast/Mattress, Thermometer, Scales, Iron strip, Rubber gasket, Zinc anode, Calliper, Camera, ATK, Grinder, Epoxy, and Scissors/cutter.

Data was obtained in the form of quantitative data from laboratory test results include chemical composition, electrochemical potential value (V), and electrochemical efficiency value (Ah/kg) analyzed and compared with DNV standard.

3. Results and Discussion

This research started with the manufacture of zinc anode products using a zinc anode material. There are several stages on how to recycle, among others:

3.1. Preparing materials to be recycled (zinc anode) used

This material is obtained from zinc disposal waste from vessels that is docking. In accordance with the provisions of SOLAS and the provisions of the Classification Bureau of the vessel, which performs the annual dock, must perform zinc anode replacement.

3.2. Preparing the smelting equipment (furnaces, steel pans, fuel, scoop, tongs and other equipment)

This equipment must be available before starting the smelting work to make the smelting work process runs smoothly and safely.

3.3. Set up printing equipment

Mattress used for this research is sand casting, by sprinkling the powder on the mattress and then fill in the sand and solidify it by adjusting the shape of the mat. The compacting is done evenly to get the desired result

3.4. Melting Process

The melting of the material is carried out on a steel skillet above the furnace by directing the combustion directly on the material to be melted. Fuel used by LPG gas. The heated material melts at a temperature of 609° C in approximately 30 minutes and then stirs well and separates the dirt that floats on the surface of the already melted material.

3.5. Pouring

Pouring is done with a careful heart, by inserting the liquid material in the sand casting hole. The material liquid is put into the cast until it is full.

3.6. Opening the cast

After the material is put into the cast, the ingredients will be cooled for about 5 minutes, then the cast can be dismantled to retrieve the printed zinc anode results.

3.7. Finishing

The end of the zinc anode recycling casting work is to do the finishing including checking and smoothing.

Zinc anode testing was conducted in corrosion laboratory and material failure of Ten November Institute of Technology Surabaya. The tests were performed using DNV ((Det Norske Verity) standard to test the material characteristics [9].

3.8. Testing the chemical composition that is contained in the zinc anode.

The compositions tested include Zn (Zinc), Al (Aluminium), In (Indium), Cd (Cadmium), Fe (Iron / Ferro), Cu (Copper), Pb (Led / Plumbumb).

From the tests performed, the results are as listed in the table below.

Table 1. Comparison between DNV standard compositions with laboratory test results

Chemical Composition	Result (%Wt) Std DNV	Result (%Wt) Lab
Zn	rem	99.300
Al	0.10-0.50	0.333
In	na	0.002
Cd	≤0.07	0.029
Fe	≤0.005	<0.002
Cu	≤0.005	0.021
Pb	≤0.006	0.015

Table 1 illustrates that the Zn composition of the tested product is 99.300% Wt and this proves the Zinc compound is excellent. Aluminium Composition 0.333% Wt is in the range between 0.10-0.50% Wt indicating under normal conditions. Indium composition is not specified on the standard while the results of the lab test are 0.002% Wt. Standard Composition Cadmium ≤ 0.07% Wt is 0.029% Wt in accordance with the provisions. Copper Composition Standard ≤ 0.005% Wt turns out in the laboratory test 0.021% Wt as well as the standard value of Plumbumb composition ≤ 0.006% Wt on laboratory test 0.015% Wt. Of the eight chemical compositions, Copper has a difference of 0.016% Wt and Plumbumb 0.009% Wt. Since both are the last compositions of relatively small values in Zinc Anode material, they are still categorized as normal.

3.9. Potential Electrochemical Testing and Electrochemical Efficiency

The results of testing the characteristics of Electrochemical Potential and Electrochemical Efficiency are as in Table 6.

Table 2. Comparison of Potential Electrochemical and Electrochemical Efficiency between DNV standard and Laboratory test results

Characteristics	DNV Standard	Test in Lab
Electrochemical Potential (V)	≤ -1.00	-1.07
Electrochemical Efficiency (Ah/kg)	780	842

Referring to the DNV standard that the required potential electrochemical quantity is ≤ -1.00 , while the test result shows -1.07, it means that the electrochemical potential in the recycled zinc anode is adequate (or qualified). Similarly, electrochemical efficiency at a minimum standard is 780 whereas in a recycled zinc anode shows 842, it can be defined that it is adequate with the required standard.

4. Conclusions

Process for the zinc anode by recycling zinc anode former takes approximately 30 minutes and a melting temperature of 609 °C to obtain a higher percentage of remaining zinc 99.30%. The results of laboratory tests on the chemical composition performed in the laboratory of corrosion and material failure Institute of Technology (ITS) Surabaya, is normal, which means that the recycled zinc anode can be used as protection / cathode protection in preventing corrosion on ships.

References

- [1] Singh R 2014 *Corrosion control for offshore structures, cathodic protection and high efficiency coating* First Edition (Elsevier BV) 131
- [2] Yamamoto N and Ikegami K 1998 A study on the degradation of coating and corrosion of ship's hull based on the probabilistic approach *Eng.ASME* **120** 121
- [3] Wan H and Huangfu W 2017 Influence of sea mud state on the anodic behavior of Al-Zn-In-Mg-Ti sacrificial anode **136** 11
- [4] Vazdirvanidis A and Pantazopoulos 2017 Corrosion investigation of stainless steel water pump components *Engineering Failure Analysis* **82** 466
- [5] Shengping Q and Weicheng C 2003 Effect of corrosion models on the time-dependent reliability of steel plated elements *Marine Structure* **16** 15
- [6] Carmona J and Garces P 2015 Efficiency of a conductive cement-based anodic system for the application of cathodic protection, cathodic prevention and electrochemical chloride extraction to control corrosion in reinforced concrete structures *Corrosion Science* **96** 102
- [7] Jia M Y and Zhang Z M 2017 PANI-PMMA as cathodic electrode material and its application in cathodic polarization antifouling *Electrochemistry Communication* **84** 57
- [8] Ferdian D and Pratesa Y 2017 Development of Al-Zn-Cu Alloy for low voltage aluminum sacrificial *Procedea Engineering* **184** 418
- [9] Det Norske Veritas 2010 *Recommended practice Dnv-Rp-B401 cathodic protection design* (Norway - Det Norske Veritas) 27
- [10] Fleury P 2014 *Performance Metal Product*. Bechtelsville : Sci Cast Company
- [11] Spengler T and Püchert H 1997 Environmental integrated production and recycling management *European Journal of Operational Research* **97** 308
- [12] Rosebrock C and Bracke S 2017 Comparison and evaluation of concepts for a future recycling process regarding attrited lead anodes used in the electrowinning process of non-ferrous metals *Procedia Manufacturing* **8** 627-634

Artikel 25

ORIGINALITY REPORT

18%

SIMILARITY INDEX

14%

INTERNET SOURCES

13%

PUBLICATIONS

%

STUDENT PAPERS

PRIMARY SOURCES

1	rules.dnvgl.com Internet Source	3%
2	www.er-c.org Internet Source	2%
3	www.coursehero.com Internet Source	2%
4	en.indotrading.com Internet Source	2%
5	N. Yamamoto, K. Ikegami. "A Study on the Degradation of Coating and Corrosion of Ship's Hull Based on the Probabilistic Approach", Journal of Offshore Mechanics and Arctic Engineering, 1998 Publication	2%
6	O Gómez, H Aponte, E Vera, Y Pineda. "Evaluation of corrosion inhibitor simulating conditions of operation", Journal of Physics: Conference Series, 2017 Publication	1%

7	Deni Ferdian, Yudha Pratesa, Inez Togina, Ira Adelia. "Development of Al-Zn-Cu Alloy for Low Voltage Aluminum Sacrificial Anode", Procedia Engineering, 2017 Publication	1%
8	ir.nimte.ac.cn Internet Source	1%
9	real.mtak.hu Internet Source	1%
10	clarknet.eng.umd.edu Internet Source	1%
11	www.zhenghaichem.com Internet Source	<1%
12	A. Vazdirvanidis, G. Pantazopoulos, A. Rikos. "Corrosion investigation of stainless steel water pump components", Engineering Failure Analysis, 2017 Publication	<1%
13	iptek.its.ac.id Internet Source	<1%
14	Z Said, M Sajid H, A Kamyar, R Saidur. " Experimental investigation on the stability and density of TiO , Al O , SiO and TiSiO ", IOP Conference Series: Earth and Environmental Science, 2013 Publication	<1%

15

Fengling Liu, Jie Zhang, Caixia Sun, Zhenhua Yu, Baorong Hou. "The corrosion of two aluminium sacrificial anode alloys in SRB-containing sea mud", Corrosion Science, 2014

Publication

<1%

16

Elizabeth Royston, Ayan Ghosh, Peter Kofinas, Michael T. Harris, James N. Culver. "Self-Assembly of Virus-Structured High Surface Area Nanomaterials and Their Application as Battery Electrodes", Langmuir, 2008

Publication

<1%

Exclude quotes Off

Exclude matches Off

Exclude bibliography On